



INDUSTRIAL ASPHALT FOOTPATH (IAF)






INDUSTRIAL CONCRETE FOOTPATH WITH ASPHALT SURFACE (ICAF)

GENERAL NOTES

- 1. FOOTPATH CROSS FALLS SHALL NOT BE FLATTER THAN 1:80 (1.2%) OR STEEPER THAN 1:40 (2.5%). CROSS FALLS GREATER OR LESS THAN SHOWN MUST BE APPROVED BY COUNCIL'S SUPERVISING OFFICER.
- 2. TO BE READ IN CONJUNCTION WITH COUNCIL SPECIFICATIONS
- 3. TYPE OF FOOTPATH TO BE AGREED BY COUNCIL ENGINEER.
- 4. AT ALL TIMES FOOTPATH WORKS SHALL NOT REDUCE PEDESTRIAN SAFETY. ADEQUATE SAFETY MEASURES MUST BE INSTALLED.
- 5. REFER YSD 402 -- FOOTPATH DETAILS FOR RETAIL STRIPS.
- ALL CONCRETE SHALL BE 25 MPa AT 28 DAYS
 (TO BE CHARCOAL COLOUR AT THE RATIO OF
 1 BAG (25kg) FOR EVERY CUBIC METRE OF CONCRETE).
- 7. FOR (CF) & (ICAF) FOOTPATH PROVIDE DUMMY JOINTS AT INTERVAL OF 1.5m AND EXPANSION JOINTS @ 15m. DUMMY JOINTS SHALL BE FINISHED WITH APPROVED JOINTING TOOL TO GIVE A NEAT GROOVE AT LEAST 6mm DEEP BY 3mm WIDE NORMAL TO THE PAVEMENT EDGE.



RESIDENTIAL FOOTPATH STRIP AND RESHEET

Yarra Standard: YSD401 Drawing Title:

TYPICAL FOOTPATH DETAILS

Richmond Town Hall 333 Bridge Road Richmond PO Box 168 Richmond 3121 Phone (03) 9205 5010 Fax (03) 8417 6666